



## TECHNICAL DATA SHEET

### Black

<b>Description</b>	Black free flowing powder
<b>Pigment Type</b>	Platelets of mica coated with black iron oxide
<b>INCI Name</b>	Mica (and) CI77499

Chemical Composition	By weight (%)	CAS	CI Number	Einecs
Mica	25-35	12001-26-2	77019	310-127-6
Black Iron Oxide	65-75	1317-61-9	77499	215-277-5

Trace Elements	Value max.	Unit
<b>Antimony (Sb)</b>	2	ppm
<b>Arsenic (As)</b>	1	ppm
<b>Cadmium (Cd)</b>	1	ppm
<b>Chromium (Cr)</b>	100	ppm
<b>Copper (Cu)</b>	50	ppm
<b>Lead (Pb)</b>	10	ppm
<b>Mercury (Hg)</b>	1	ppm
<b>Nickel (Ni)</b>	200	ppm
<b>Zinc (Zn)</b>	50	ppm

	Specification	Unit
<b>PH</b> (10 % aqueous solution)	4-11	pH
<b>Particle size</b> (90 % within the range)	10-60	µm
<b>Loss on drying</b> (105 °C)	< 0,5 %	%



	<b>Specification</b>	<b>Unit</b>
<b>Density</b> (g/cm <sup>3</sup> )	2,9–3,5	g/cm <sup>3</sup>
<b>Oil Absorption</b>	n. a.	g/100 g
<b>Total amount of bacteria</b>	< 100	cfu/g
<b>Yeast and Mould</b>	< 100	cfu/g
<b>Pathogens</b>	negative	
<b>Color/Luster</b>	visual	

The above information is the result of the quality check of our producer/supplier. They don't free the processor from own tests and the implementation of an entrance check. A legal binding assurance of certain characteristics or suitability for a specific purpose cannot be derived from this information. Any intellectual property rights as well as existing laws and regulations must be observed by the recipient under his own responsibility.

This TDS is electronically generated and is therefore valid without a signature.